



CSX.0026

CONSILEX SAN

Re-alkalising, reinforcing,
protective, hardener for concrete

Customs Code

3824 9970

Packaging

- Plastic can 5 kg
- Plastic can 10 kg
- Plastic can 25 kg
- Pallet tank (IBCs) 1000 kg

Application

- Sprayer
- Low pressure airless nebulizer

Family
Consilex

Product Lines

- Infratech
- Sanageb

Components
Single-component

Type
Realkalising and migratory corrosion inhibitor for concrete structures

Functional Categories

- **Repair and restoration of concrete structures with thixotropic mortars**
- **Block repair of concrete works with free-flowing mortars**
- **Structural maintenance of dams, reservoirs, ducts and water ducts**
- **Structural maintenance of bridges and viaducts**
- **Realkalinization and renovation of existing cement conglomerates**

Appearance
Liquid

General description

Reactive, colourless mineral solution for preliminarily re-alkalising and reinforcing concrete surfaces to be restored. It is an inorganic, mineral compound chemical affine with concretes. It reacts with alkali hydrates alkaline and with water, present in the porosity of concretes, mortars and plasters, forming stable silicate gels, which hermetically and lastingly seal the capillary lattice.

General features

CONSILEX SAN waterproofs and reinforces the conglomerate both at superficial level and in more internal layers, preventing the penetration of water, harsh solutions etc., it protects the structures from the consequences of freeze-thaw cycles, from harsh processes resulting from the use of antifrost de-icing salts in road works, further facilitating the removal of ice incrustations.


Dosage

Apply from 0.15 to 0.30 kg of CONSILEX SAN per square metre of surface to be treated.


Fields of application


Through re-alkalisation, hardening, consolidation, conservative maintenance of plasters to base lime and cement, concrete, paving, reservoirs, pipes, tanks, vessels, bridges, viaducts, tunnels, retaining walls, parking areas, airport runways and motorway.


Basic features


 Density:
1.02 kg/dm³

 Nonflammable

 Shelf-life:
12 months

 Solvent-free

 Temperature of use:
+5 / +35 °C

 Available colours
Transparent

Technical specifications

Active substance: > 25 %

Depth of penetration: 2-6 mm

pH: 12 _

IF YOU WANT TO SOLVE IT
 **azichem**

www.azichem.com

Updated: **10/01/2022**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Tools cleansing

- Water

Applicable on

- Plasters
- Concrete
- Prefabricated concrete
- Fiber-cement

Substrate preparation

Accurate dedusting and saturation with water, for achieving the condition "dry surface saturation". Saturation is particularly important: the product reacts with substances placed in water solution and uses the same water for forming the gel.

Instructions for use

Spray-apply with a low pressure airless pump on cement surfaces to be treated.

For deep reinforcement, apply several coats taking care to apply each coat when the previous begins to dry out.

It can dull aluminium and glass surfaces, ceramised tiles, etc., which must then be protected by taping or other, during application.

Do not apply on mineral surfaces (like plaster and bricks) destined to be visible, without carrying out a preliminary test, as you latent salts may crystallise!

Storage and preservation

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Protect from humidity.



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.



www.azichem.com

Updated: **10/01/2022**

General sales conditions and legal notices on

www.azichem.com/disclaimer

CONSILEX SAN is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **10/01/2022**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**