

FLR.0210 UNIKOLL

Mono-component adhesive based on hydraulic binders

Customs Code

3824 5090

Packaging

- Bag 25 kg

- Pallet: 50 x (Bag 25 kg)

Application

- Notched finishing trowel

Family Type

Floortech Adhesives and stucco

Product Lines Functional Cathegories

· Bonding and filling tiles, parquet, etc. Building

 Opus Floor

> Components Appearance

Single-component **Powder**

Certifications and legislations



EN 12004-1:2017

Adhesives for ceramic tiles C2TE

General description

A certified single-component cementitious adhesive with a base of hydraulic binders free from harmful additives, containing starch-derived adhesion promoters, selected siliceous and calcareous sands, reactive fillers with high pozzolanic activity and cellulosic thickeners for bonding tiles, ceramics, stoneware and natural and/or reconstructed stones on horizontal and vertical surfaces, for use both internally and externally. Cannot be used for plaster or anhydride substrates nor for substrates subject to movement or bearing a protective film.

Dosage

Use from 3 to 5 kg/m² of UNIKOLL depending on the type of support and the type of material to be bonded.

Fields of **application**

Bonding of tiles, ceramics, stoneware, natural and/or reconstructed stones, etc. on horizontal and vertical surfaces, internal and external. Regularisation finishings. Modular element bonding and smoothing for insulating cladding: polystyrene sheets, wood panels- magnesium panels, wood-cement, etc. Do not use for: - Substrates in gypsum or anhydrite - Substrates subject to movements - Substrates with protective films or coatings

Basic **features**

Maximum diameter of aggregate: 0.4 mm

Mix with water:

Pot-life: 60 min

Shelf-life: 8 months

Temperature of use: +5 / +30 °C

Available colours

Technical specifications

Adesione a trazione iniziale (UNI EN 1348): 1 N/mm²

Adesione a trazione trascorsi 30' (UNI EN 1346): 0.6 N/mm²

Scivolamento (UNI EN 1308): ≤ 0.1 mm

Durability - Tensile adhesion after freeze-thaw cycles (UNI EN

1348): > 1 N/mm²

Durability - Tensile adhesion after immersion in water (UNI EN

1348): > 1 N/mm²

Durability - Tensile adhesion after thermal aging (UNI EN

1348): > 1 N/mm²



www.azichem.com

Updated: 29/07/2022

General sales conditions and legal

notices on

www.azichem.com/disclaimer

Page: 1/3

Tools **cleansing**

• Water

Applicable on

- Concrete
- Prefabricated concrete
- Tuff
- Brickworks
- Stone walls
- Tiles
- · Floor screed

Substrate **preparation**

The surfaces of application have to be properly cured, conveniently roughened, clean, free of any soiling whatever its nature, crumbling and non-adhering parts, dust etc. Any traces of oils, greases, release agents, waxes, paints, etc., as well as any anti-adhesive substance, should be preliminarily removed.

Instructions for use

For each 25 kg bag of UNIKOLL, add 6-6.3 litres of clean water and mix thoroughly, with a mechanical stirrer, until a homogeneous lump-free mixture is obtained. After waiting a few minutes, stir and spread the adhesive with a toothed adhesive spreader.

The products (tiles or other coatings) should be applied with a slight pressurised movement for the entire surface to be in perfect contact with the adhesive. Any adjustment must be made within 10-12 minutes of laying. For applications outdoors, apply a continuous layer of adhesive also on the back of the item.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.





www.azichem.com

Updated: **29/07/2022**General sales conditions and legal

notices on

www.azichem.com/disclaimer

Page: 2/3

Warnings, Precautions and **Ecology**

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

Do not apply in case of direct exposure to sunlight and/or rain. Cure the protection for at least $24\ \mathrm{hours}$.

UNIKOLL is produced/distributed by





www.azichem.com

Updated: **29/07/2022**

General sales conditions and legal

notices on

www.azichem.com/disclaimer

Page: 3/3