



Family
Intotech

Type
Preliminary salt-resistant rendering fixative

Product Lines
• **Building**

Functional Categories
• **Repair and restoration of concrete structures with thixotropic mortars**
• **Masonry plastering with plasters and skims**
• **Renewal of wet masonry with waterproofing plasters**

Components
Single-component

Appearance
Powder

INT.0127

REPAR PLUG

Super-adhesive rendering for cement or minimally absorbing supports

Customs Code

3824 5090

Packaging

- Bag 25 kg

Application

- Finishing trowel
- Plastering machine


General description

A single-component, super-adhesive cementitious mortar for rough coating, with a base of high-strength binders, selected aggregates, adhesion-promoting polymers and specific agents. Ideal for the preliminary "rough coat" treatment of concrete surfaces, mixed masonry, rock walls and other poorly-absorbent surfaces, for subsequent coating with traditional (INTOSANA), dehumidifying (SANATIGH) and/or thermal-insulating (SANAWARME or CALEOSANA) plasters.

Fields of application

Gripping rendering for subsequent plasters, both based on cement and hydraulic lime; protective coatings, renovation of works and structures in reinforced concrete.

Basic features


 Dosage:
4-6 kg/m²

↔ Max. recommended thickness:
30 mm


 Maximum diameter of aggregate:
0.7 mm


→|← Min. recommended thickness:
5 mm

 Nonflammable

 Pot-life:
60 min

 Shelf-life:
12 months

 Temperature of use:
+5 / +35 °C

 Available colours
Gray

Technical specifications

Adhesion to substrate (UNI EN 1015-12): > 2.5 N/mm²

Compressive strength (UNI EN 1015-11): > 40 N/mm²

Flexural strength (UNI EN 1015-11): > 8 N/mm²

pH: > 12 _

Static elastic modulus (EN 13142): 17000 N/mm²

Tools cleansing

• Water

Applicable on

- Plasters
- Concrete
- Cement-based or lime-based mortars
- Prefabricated concrete
- Fiber-cement
- Bricks
- Mixed walls (bricks and stones)
- Stone walls
- Rock walls

IF YOU WANT TO SOLVE IT
 **azichem**

www.azichem.com

Updated: 29/11/2021

General sales conditions and legal notices on

www.azichem.com/disclaimer

Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., conveniently saturated with water until they reach the condition "saturated with dry surface".

Instructions for use

Pour about 2/3 of the mixing water into the mixer, add REPAR PLUG and the remaining water; continue to mix until a homogeneous lump-free mixture is obtained. The mixing water should be about 16-18% of the weight of the bag. After mixing is completed wait a few minutes before applying the product by "spraying" ("scratch coat"), by brick trowel and plastering trowel or plastering machine. The scratch coat, applied by "spraying", must provide a corrugated surface to promote the grip of the plaster that must be applied promptly: within 2-3 days.

In the case of successive dehumidifying (SANATIGH) or insulating (SANAWARME or CALEOSANA) plasters, hold the sprayed surface, "open" (non-homogeneous over the entire surface).

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

Do not apply in case of direct exposure to sunlight; cure the protection and the prolonged moist hardening of exposed surfaces.



www.azichem.com

Updated: 29/11/2021
General sales conditions and legal notices on www.azichem.com/disclaimer

REPAR PLUG is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **29/11/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**