



OSM.0088

OSMOCEM RD

Osmotic deformable two-component thick waterproofing cement

Customs Code

3824 5090

Packaging

- Bag 25 kg [A]
- Plastic can 5 kg [B]
- Kit: 1 Bag 25 kg [A] + 1 Plastic can 5 kg [B]

Application

- Brick trowel
- Finishing trowel
- Spatula
- Plastering machine

Family
Osmocem

Product Lines

- Aqua
- Building
- Infratech

Components
Two-components

Type
Osmotic two-components cements

Functional Categories

- Osmotic waterproofing
- Structural maintenance of dams, reservoirs, ducts and water ducts
- Renewal of wet masonry with waterproofing plasters

Appearance
Powder + Liquid

Certifications and legislations



EN 998-1

Specification for Mortar for Masonry - General purpose rendering/plastering mortar (GP)

General description

Osmotic fibre reinforced two-component cement mortar, based on hydraulic binders, modifying resins and flexibilisers, superpozzolanic reactive fillers, for the preparation of adhesive mixtures, easy to spread, which after hardening, provide an effective waterproofing protection, both in direct push and in negative pressure, with high capacity of deformation.

General features

OSMOCEM RD synergistically brings together properties and benefits derived from the peculiar mix of components, which include superpozzolanic reactive fillers, for a net improvement of the chemical inertness and adherence, the reduction of porosity and permeability, with consequent reduction of carbonation. Suitable polymers present in the mixture also increase its deformability and stability, reducing scraps, detachments and cracks.

Dosage

Approximately 18 kg/m² of OSMOCEM RD for every centimetre of thickness to be implemented (approximately 1800 kg per cubic metre).

Fields of application

Coatings, reconstructions and millimetric shields, finishing coats etc., in interventions to restore conservative, waterproofing works in reinforced concrete, wall coverings, extended exposed surfaces etc. provided they are sufficiently porous and absorbent and free from any waterproofing and / or water-repellent surface treatment, whether chemical (siloxanes, epoxies, polyurethanes, etc.) or natural (wax-up). Particularly indicated for interventions of dehumidification and anti-condensation rehabilitation of underground spaces, in combination with the dehumidifying cycle with CALEOSANA.

Basic features



Highlighted product



Max. recommended thickness:
15 mm



Maximum diameter of aggregate:
1 mm



Min. recommended thickness:
5 mm



Nonflammable



Pot-life:
50 - 70 min



Shelf-life:
12 min



Temperature of use:
+5 / +35 °C



UV-resistant



Available colours
Gray

IF YOU WANT TO SOLVE IT
 **azichem**

www.azichem.com

Updated: 13/05/2022
General sales conditions and legal notices on
www.azichem.com/disclaimer

Technical specifications

Bonding force (UNI EN 1015-12): 2.4 N/mm²

Capillary absorption (UNI EN 1015-18): 0.09 kg•h^{0.5}/m²

Compressive strength (UNI EN 1015-11): > 40 N/mm²

Darcy impermeability: 10⁻¹⁰ cm/s

Density (UNI EN 1015-6): 1900 kg/m³

Flexural strength (UNI EN 1015-11): > 8 N/mm²

Static elastic modulus (EN 13142): 19000 N/mm²

Tools cleansing

- Water

Applicable on

- Concrete
- Bricks
- Mixed walls (bricks and stones)
- Stone walls
- Rock walls

Substrate preparation

Application surfaces should be clean, free of soiling, crumbling and non-adhering parts, dust, etc., water repellent treatments in general, etc. conveniently saturated with water until they reach the condition "saturated with dry surface". It is always advisable to prime the application support with approximately 100-150 g / m² of COMPONENT B adhesive latex; in this way, at least three extraordinarily effective operations are carried out with a simple and fast priming: a) expulsion of the air from the surface porosity _ stopper (with a drastic reduction of the well-known blistering that occurs on elastic products with low thickness); b) decrease in the absorption of the support (to guarantee a suitable curing of the waterproof skin coat); c) increased adhesion thanks to the deep penetration of the polymeric component.

Instructions for use

Mix the powder component (component A) with the hydrating solution (component B) with a drill at a low number of revolutions, pouring the powder progressively in the liquid, continue mixing until a homogeneous lump-free mixture is obtained. After mixing is completed wait a few minutes and stir again before proceeding with application.

To further improve the performance of the coating, insert a steel reinforcement mesh (wire 2 mm mesh and 5x5 cm) between layers.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



www.azichem.com

Updated: 13/05/2022
General sales conditions and legal notices on www.azichem.com/disclaimer

Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

It is always essential to carry out preliminary tests to verify the appropriateness of the product, depending on specific requirements.

Do not apply in case of direct exposure to sunlight and cure the protection and moist hardening.

Do not apply on little or non-porous substrates or previously coated with water-repellent treatments in general, if not after appropriate roughening by bush hammers, sanders and equipment suitable for preparatory treatments of substrates, or after appropriate treatment with suitable polymeric primers.

OSMOCEM RD is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **13/05/2022**
General sales conditions and legal
notices on
www.azichem.com/disclaimer