



PRS.0101

## PROTECH FLEX

Polyurethane sealant in a cartridge with a high modulus of elasticity

### Customs Code

3909 5090

### Packaging

- Cartridge 600 cc
- Cartridge 300 cc
- Box: 12 x (Cartridge 300 cc)
- Box: 20 x (Cartridge 600 cc)

### Application

- Apply by hand
- Dispensing gun

Family  
**Proseal**

Product Lines

- Aqua
- Building
- Infratech
- Floor

Type  
**Plastic and elasto-plastic sealants**

Functional Categories

- **Transparent waterproofing of tiled terraces and balconies**
- **Osmotic waterproofing**
- **Waterproofing with hot-sprayed elastomeric coatings (100% pure polyurea)**
- **Waterproofing underground structures with hydro-expansive products**
- **Construction of high performance industrial concrete floors**
- **Waterproofing control joints or construction joints**
- **Horizontal cement waterproofing of terraces and balconies**
- **Prefabrication**
- **Plastering and loose-fill of cracks and cavities on plasters and facades**
- **Elastomeric sealing of expansion and shrinkage joints on concrete floors and screeds**

Components  
**Single-component**

Appearance  
**Paste**

## Certifications and legislations



**EN 15651-1:2012**

Sigillanti per giunti per impiego non strutturale negli edifici e piani di camminamento pedonali



**ÉMISSIONS DANS L'AIR INTÉRIEUR**

A + (very low emissions)

## General description

A single-component, moisture-curing and fast-hardening polyurethane sealant with a medium-to-high modulus of elasticity, remaining permanently elastic yet with high surface hardness and being tear- and weather-resistance and paintable. Ideal for the deformable sealing of expansion joints on terraces and balconies, for filling joints on prefabricated walls and on wooden, steel, aluminium, copper and plastic materials along with plasters and so on.

## General features

- Free from solvents, PVC, halogenated compounds, odourless.
- Permanently elastic, high resistance to razing and to the atmosphere.
- Free of shrinkage and dimensionally stable.
- High thixotropy: it does not drip and does not create burrs. Easy workability.
- It is not sticky and does not accumulate dust and dirt.
- Over-paintable after polymerisation has been completed.

## Dosage

Indicative consumption with a 300 cc PROTECH FLEX cartridge: 5x2,5 mm joint = 20 linear metres; 10x5 mm joint = 6 linear metres; 15x7,5 mm joint = 2,5 linear metres; 20x10 mm joint = 1.5 linear metres

## Fields of application

The high versatility and excellent adhesion to different media make PROTECH FLEX the most suitable adhesive sealant for flooring and roofing joints made of concrete, wood products, steel, stainless steel, aluminium, anodised aluminium, galvanized steel sheets, copper, plastics, etc.



[www.azichem.com](http://www.azichem.com)

Updated: **30/11/2021**  
General sales conditions and legal notices on [www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)

## Basic features



Density:  
1.30 ( $\pm 0.05$ ) g/cm<sup>3</sup>



Nonflammable



Shelf-life:  
12 months



Temperature of use:  
+5 / +35 °C



Use wearing protective gloves



UV-resistant



Available **colours**  
Request available colors

## Technical specifications

*Breaking load longitudinal (DIN 53504): 1.5 N/mm<sup>2</sup>*

*Complete hardening (a 20°C): 24 h*

*Dry residue (10' a 150°C):  $\geq 95$  %*

*Hard to touch (a 20°C): 60 min*

*Hardness (DIN 53505 - Shore A): 40 \_*

*Longitudinal elongation at break (DIN 53504):  $\geq 300$  %*

*Static elastic modulus (DIN 53504): 0.6 N/mm<sup>2</sup>*

*Working temperature -40: +80 °C*

## Tools cleansing

- Nitro thinner

## Applicable on

- Plasters
- Concrete
- Cement-based or lime-based mortars
- Prefabricated concrete
- Drywall
- Wood
- Metal surfaces
- Plastic
- Fiber-cement
- Tiles
- Floor screed

## Substrate preparation

The application supports must be perfectly clean and dry, free from dust and soiling. Preliminarily treating the side walls of the joint with the appropriate primer single-component polyurethane PROTECH FLEX PRIMER.

It is appropriate to provide for inserting into the joint, whatever its nature, the specific foamed polyethylene kerb FILTENE FONDOGIUNTO, of the appropriate size to the joint to be sealed.

Prepare an easily removable paper ribbon (coachbuilder ribbon type) on both sides of the joint, in order to prevent the sealant overflowing outside of the natural seating of the joint.

## Instructions for use

Slowly and carefully extrude the sealant from the cartridge in the specially prepared seat of the joint, with the appropriate gun (of the type for silicone). Before the total hardening of the sealant, spread it to the brim with spatula on the surface of the joint. After hardening, remove the adhesive tape.

Clean any product overflows from the seat of the joint with suitable solvents (like acetone or Nitro thinner).

## Storage and preservation

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity. Store the product at a temperature between +5°C and +35°C.



IF YOU WANT TO SOLVE IT

[www.azichem.com](http://www.azichem.com)

Updated: **30/11/2021**  
General sales conditions and legal  
notices on  
[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)



## Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: [www.azichem.com](http://www.azichem.com). The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: [www.azichem.com](http://www.azichem.com).

It is forbidden to dispose of the product and/or packaging in the environment.

Carry out preliminary adhesion and compatibility tests of paints in case of subsequently painting the sealant.

It is good practice for the depth of the sealing section not to exceed half the width of the joint. To this end, the depth will be determined by the placement of FILTENE FONDOGIUNTO.

*PROTECH FLEX is produced/distributed by*



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy  
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



[www.azichem.com](http://www.azichem.com)

Updated: **30/11/2021**  
General sales conditions and legal notices on  
[www.azichem.com/disclaimer](http://www.azichem.com/disclaimer)