



SYN.0382

SYNTECH PU FOAM 30

Closed cell expanded
polyurethane covering of 30
kg/m³

Packaging

- Barrel 250 kg [A]
- Barrel 215 kg [B]
- Kit: 1 Barrel 250 kg [A] + 1 Barrel 215 kg [B]

Application

- Two-components hot sprayer

Family
Syntech

Product Lines

- Aqua
- Building
- Infratech

Components
Two-components

Type

Epoxy and polyurethane primers, treatments and coatings

Functional Categories

- **Structural maintenance of dams, reservoirs, ducts and water ducts**
- **Structural maintenance of bridges and viaducts**
- **Protective, strengthening, polyurethane or epoxy coatings**

Appearance

Liquid + Liquid

General description

Syntech PU Foam 30 is an expanded polyurethane with a nominal density of 30 kg per m³; it is a closed cell foam, developed using a new generation blowing agent designed to adhere to various supports and capable of providing both excellent thermal insulation and minimizing air leaks. As part of a system, it has been designed as a closed cell, tested and evaluated for use as a composite system to provide a complete air barrier and to provide exceptional performance in reducing heat transfer, achieving incredible benefits such as minimizing the humidity transmission and air leaks. The performance of Syntech PU Foam 30 has been evaluated on iron, sheet metal, steel, glass, concrete and wood as a composite system or together as a single system.

General features

Syntech PU Foam 30 guarantees adhesion with excellent support, giving rise to a continuous membrane, without any joints and extremely resistant: - It adapts to any geometric shape - Friend of the environment, they are inert and disposable materials. - Does not weigh down the structure - Low permeability - Better thermal insulation - Reduced thicknesses compared to other insulators - Elimination of thermal bridges - Long life - useful life exceeding 50 years. - Excellent compressive strength - Resistant to biological attack and does not favor the growth of fungi and bacteria

Dosage


Approximately 0.350 kg of Syntech PU Foam 30 for each square meter of surface to be coated and for each centimeter of thickness to be created


Fields of application

Syntech PU Foam 30 expanded polyurethane is particularly used for: - Thermal insulation on buildings, attics, ceilings - Waterproofing following the use of top covering coating - Coating of foundations - Coating of cisterns and reservoirs - Coating of isothermal vans - Protection of pipelines and pipes - Cold room lining - Coating and protection of sheet metal.

Basic features


 Density:
1.12 g/cm³

 Shelf-life:
12 months

 Temperature of use:
+10/+30 °C

 Use wearing protective glasses

 Use wearing protective gloves

 Available colours
Neutral tending to yellow

IF YOU WANT TO SOLVE IT
 **azichem**

www.azichem.com

Updated: 27/09/2023

General sales conditions and legal notices on

www.azichem.com/disclaimer

Page: 1/3

Technical specifications

Capillary absorption (EN 1609:2013): 0.18 kg/m²

Compressive strength (EN 826): CS(10/Y) da 150 kPa

Density determination (EN 14315-1:2013): 30 kg/m³

Fire resistance (EN 13501-1:2009): CLASS E _

Gel time (EN 14315-1:2013): 12 s

Hard to touch (EN 14315-1:2013): 14 s

Tools cleansing

- Thinner for resins

Applicable on

- Concrete
- Prefabricated concrete
- Wood
- Metal surfaces
- Fiber-cement
- Glass
- Steel

Substrate preparation

All surfaces must be free of contaminants and humidity less than 3%; it must offer a mechanical grip on a solid and non-yielding support. Where necessary, we recommend preparation using shot peening, bush hammering, sanding or hydrowashing. Consult personnel for correct preparation of the support. It is recommended to use, if necessary, primers from the Syntech family and contact the staff for clarification on the most suitable type to use.

Instructions for use

Syntech PU Foam 30 requires a bimixer system capable of producing pressure over 160 bar and temperatures over 60 °C, equipped with transfer pumps with a 3:1 ratio. Contact the staff for clarification on the best gun to use and details relating to the air system. The two components must be preheated to around 30 °C using heating bands. Syntech PU Foam 30 must be sprayed at pressures that fall within the range of 140 -160 bar and at temperatures that can vary from 35 to 45 °C. It is the applicator's responsibility to correctly calibrate the technical equipment taking into account the combination of nozzles relating to the gun, the length of the hoses and the technical parameters of the spray system. Syntech PU Foam 30 must not be applied in thicknesses greater than 3 cm per coat. The next step should not be carried out before 30 minutes have passed since the previous application, giving the material time to cool.

Storage and preservation

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Store the product at a temperature between +10°C and +30°C.

Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com. It is forbidden to dispose of the product and/or packaging in the environment.



www.azichem.com

Updated: 27/09/2023
General sales conditions and legal notices on www.azichem.com/disclaimer

SYNTECH PU FOAM 30 is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **27/09/2023**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**