

STABILCURE

CHARACTERISTICS

Curing adjuvant based on acrylic resins in water-based dispersion, specific for the curing and anti-evaporating surface treatment of paving in natural bound and stabilized aggregate.

TECHNICAL SPECIFICATIONS

Appearance	Liquid
Colour	White
Storage life	12 months
Specific weight	1,12 kg/l
Application temperature	+5 / +35 °C

ADDITIONAL INFORMATION

Flammability	No
Cleaning tools	Water
Personal protective equipment to be used	Gloves

STORAGE

Store the product in its original container in a cool, dry place, protected from frost and direct sunlight. Inadequate storage of the product may cause the loss of its characteristics.

PACKAGE

25 kg tank

CONSUMPTION

Minimum application of 200 g/m²

APPLICATION

Low-pressure airless nebulization

FIELDS OF APPLICATION

Anti-evaporative surface treatment for protection during the curing of cycle paths, footpaths, rural roads, forest roads, paths in parks and gardens, cemetery roads, sports facilities, playgrounds, car parks, golf courses, squares, archaeological sites and any other support made of natural soil or bound and stabilized aggregate.

METHODS OF APPLICATION

STABILCURE must be applied by means of low-pressure airless nebulization on the surface of the paving, immediately after the laying and compaction, advancing progressively and consequently the implementation.

The minimum dosage to be applied is 200 g/m².

Our technical staff is available to provide useful information for the best use of the product.

WARNING

Please note that the user is required to take view of the latest Product Safety Data Sheet, containing chemical-physical and toxicological data, risk phases and other information in order to transport, use and dispose of the product and its packaging in complete safety. It must be recalled, however, that you must not dispose of the product and its packaging in the environment. The information contained in this technical data sheet, while referring to our best experience, is to be considered in any case indicative and therefore the user is recommended to carry out any test necessary to verify the suitability of product. The user is required to determine whether the product is suitable for the intended use and in any case assumes any responsibility arising from its use.

IMPORTANT RECOMMENDATIONS

The treatment with STABILCURE must be done before the surface of the paving can be subjected to premature drying by external agents: particular attention must be paid in applying the treatment immediately after the completion of the compaction of the paving in the case of particularly unfavourable conditions of exposure (strong solar radiation, high temperatures, presence of wind).

In similar cases, and as an additional precaution, the paving must be covered with non-woven fabric and kept moist for a period of 3-4 days.

The application of STABILCURE does not compensates for any defects related to an incorrect laying of the paving, such as low or excessive moisture in the mixture, the non-elimination of coarse aggregate segregation (floor cavities) or inadequate compaction. It is therefore recommended to proceed with the processing of the mixture "in a workmanlike manner".

MANUFACTURER/DISTRIBUTOR

STABILCURE is manufactured/distributed by TERRA SOLIDA, an exclusive brand of Promotec Srls.

Update of 16/05/2018.

Promotec Srls Unipersonale

Registered Office: Piazzetta Costantini, 24 33170 Pordenone PN - Betriebszentrale: Via Malignani, 33 33080 Fiume Veneto PN
Tel.: 0434 954014 - info@terrasolida.it - www.terrasolida.it